

INFINITY2®
SUSTAINABLE FABRIC

WEAVING EXCELLENCE WITH INNOVATION

Benefits of Infinity₂ include:

- 100% recyclable with active Reclamation Program that captures scrap from post-industrial (pre-consumer) and post-consumer
- Produced from 100% post-industrial (pre-consumer) recycled content
- Repeat recyclability for continued sustainability
- PVC-free
- Phthalate-free
- Lead-free
- Every component of this TPO compound is heat and chemically stable.
- Resistant to microbial and fungal growth
- Durable and washable

Dare	able and washable	201	AD (ODTI	CAL	CHCC	/C VALUE
		SOLAR OPTICAL PROPERTIES				SHGC/G VALUE g-tot (glass & blind)	
0 1	0.1	то.	D0	4.0	T) (SINGLE	INSULATING
Code	Color	TS	RS	AS	TV	1/4 CL	1 HA
	TY ₂ - 1%						
PG1	Cotton	20	68	12	18	0.29	0.22
PG2	Almond	15	61	24	12	0.31	0.23
PG3	Wheat	12	54	34	10	0.35	0.25
PG4	Stone	13	55	32	11	0.35	0.24
QG1	Barley	18	52	30	15	0.37	0.26
VG1	Nickel	8	37	55	7	0.42	0.30
VG2	Midnight	1	63	93	2	0.59	0.37
VG3	Bark	3	7	90	5	0.58	0.37
VG4	Slate	2	9	89	4	0.57	0.36
INFINI	TY ₂ - 3%						
PG1	Cotton	20	70	10	19	0.28	0.21
PG2	Almond	17	61	22	15	0.32	0.23
PG3	Wheat	12	52	36	9	0.37	0.25
PG4	Stone	12	52	36	11	0.37	0.25
QG1	Barley	16	53	31	14	0.37	0.25
VG1	Nickel	9	36	55	8	0.44	0.30
VG2	Midnight	3	6	91	5	0.59	0.37
VG3	Bark	3	7	90	4	0.58	0.37
VG4	Slate	3	10	87	5	0.57	0.36
INFINI	TY ₂ - 5%						
PG1	Cotton	23	68	9	22	0.30	0.22
PG2	Almond	20	60	20	18	0.33	0.23
PG3	Wheat	14	51	35	12	0.37	0.26
PG4	Stone	15	52	33	14	0.37	0.25
QG1	Barley	19	51	30	17	0.38	0.26
VG1	Nickel	10	34	56	11	0.45	0.30
VG2	Midnight	5	6	89	8	0.60	0.37
VG3	Bark	4	7	89	6	0.59	0.37
VG4	Slate	5	9	86	7	0.58	0.36



The Next Generation of Sustainable Fabric



PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS UL.COM/GG UL 2818



MIF Seal of Approval

















TS = Solar Transmittance

RS = Solar Reflectance

AS = Solar Absorptance

TV = Visual Transmittance

SHGC = Solar Heat Gain Coefficient

1/4 CL = 1/4" Clear Glass 1 HA = 1" Heat Absorbing Glass

Fabrics Installed Internally Zero-Degree Profile Angle

For additional performance values, test references and technical definitions visit us at www.phifer.com.



*Colors may vary based on individual computer settings and should only be used for general reference.

INFINITY₂ SPECIFICATIONS

SheerWeave Infinity₂ sustainable sun control fabrics are eco-friendly full basketweaves designed to meet the most stringent environmental design standards. With 100% recycled content, 100% recyclable, and a PVC-free composition, Infinity₂ fabrics offer the same solar heat and glare control properties as traditional SheerWeave fabrics for conserving energy, harnessing natural light and maintaining interior comfort levels.

	FIRI	Ξ
CLASSIFIC	1OITA	V

1%, 3%, 5% NFPA 701 TM#1 (small scale) NFPA 101 (Class A Rating)

CAN/ULC-S 109 (large scale) IBC Section 803.1.1 (Class A Rating)

3%, 5% ONLY BS 5867 Part 2 Type B Performance

5% ONLY CAN/CGSB2-4.162-M80

Fire classifications are subject to change. Please go to phifer.com for the most current information.

BACTERIA ASTM E 2180 ASTM G21

AND FUNGAL RESISTANCE

ENVIRONMENTAL GREENGUARD GREENGUARD Gold

CERTIFICATION Certified to these standards for low chemical emissions into indoor air during product usage

LEAD FREE RoHS/Directive 2002/95/EC REACH (EC 1907/2006) compliant

ANSI/WCMA A 100.1-2007 for lead content

US Consumer Product Safety Commission Section 101

WARRANTY 5-year interior

ACOUSTICAL NRC (Noise Reduction Coefficient) and SAA (Sound Absorption Average) tested in accordance with

PERFORMANCE ASTM C423-09a

UV PROTECTION Seal of Approval by the Melanoma International Foundation (MIF) for effectiveness in preventing sun

damage to the skin or eyes

STYLE 1% 3% 5%

WIDTHS 63" and 98" 63" and 98" 63" and 98"

160 cm and 248.9 cm 160 cm and 248.9 cm 160 cm and 248.9 cm

ROLL LENGTH 30 Linear Yards 30 Linear Yards 30 Linear Yards 27.4 Linear Meters 27.4 Linear Meters 27.4 Linear Meters

COMPOSITION 100% TPO 100% TPO 100% TPO

(Thermoplastic Olefin) (Thermoplastic Olefin) (Thermoplastic Olefin) 20% TPO fiber yarn 20% TPO fiber yarn 80% TPO coating on TPO yarn on TPO yarn (Thermoplastic Olefin) 20% TPO fiber yarn 80% TPO coating on TPO yarn on TPO yarn

MESH WEIGHT 14.63 oz/yd² 13.69 oz/yd² 12.82 oz/yd²

496.03 g/m² 464.17 g/m² 434.67 g/m²

 FABRIC THICKNESS
 0.032 in
 0.031 in
 0.030 in

 0.813 mm
 0.787 mm
 0.762 mm

OPENNESS FACTOR Approximately 1% Approximately 3% Approximately 5%

UV BLOCKAGE Approximately 99% Approximately 97% Approximately 95%

ACOUSTICAL VALUE NRC .20 / SAA .23 NRC .20 / SAA .19 NRC .10 / SAA .11





